

WAGENBORG SHIPPING B.V.

CASE STUDY

The Problem:

Customer Needs:

A high corrosion and abrasion resistant coating system. Easy to repair

On board of the RoRo ships, the weather-decks and the loading ramps are subject to high wear.

If the wear-down coating get wet it tends to get very slippery and of course rusting of the surface occurs.

The solution:

After having completed surface preparation (Blas-trac to Sa-2), the treated areas were coated to full satisfaction with a Unica System:

- | | | |
|-----------------|---|------------|
| 1. Primer | Uni-Micazinc MC Grey | DFT 75 µm |
| 2. Intermediate | Uni-Aluprotector
with Aluminium NON-skid | DFT 120 µm |
| 3. Topcoat | Uni-Aluprotector | DFT 120 µm |

